

# SABIC® HDPE F00952

## HIGH DENSITY POLYETHYLENE

### DESCRIPTION

SABIC® HDPE F00952 resin is a high molecular weight High Density Polyethylene copolymer which has been designed specifically for blown film extrusion. It has broad molecular distribution and high density combine successfully to give excellent extrudability with high film strength and rigidity. The material contains anti oxidant. Application SABIC® HDPE F00952 resin is recommended for blown film extrusion. This product is suggested for the manufacture of high strength grocery sacks, shopping bags and high quality thin films for multi wall sack liners and replacement for thin paper products. Films of this product are readily treated and printed to give high quality graphics. Processing conditions SABIC® HDPE F00952E can be extruded on conventional HMW-HDPE equipment at melt temperatures between 200 and 235 °C. Film properties Film properties have been measured at 15 µm blown film with a BUR = 4.

### TYPICAL PROPERTY VALUES

Revision 20180313

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate <sup>(1)</sup></b>			
at 190 °C and 2.16 kg <sup>(1)</sup>	0.05	dg/min	ISO 1133
at 190 °C and 21.6 kg	9	dg/min	ISO 1133
<b>Density</b>	952	kg/m <sup>3</sup>	ASTM D1505
<b>FILM PROPERTIES</b>			
<b>Dart Impact F50 <sup>(2)</sup></b>	180	g	ASTM D1709
<b>Tear strength TD Elmendorf</b>	60	g/µm	ASTM D1922
<b>Tear strength MD Elmendorf</b>	12	g/µm	ASTM D1922
<b>Tensile test film</b>			
Strain at break TD	550	%	ASTM D882
Strain at break MD	400	%	ASTM D882
Stress at break MD <sup>(2)</sup>	60	MPa	ASTM D882
Stress at break TD	56	MPa	ASTM D882
Modulus of elasticity TD	1500	MPa	ASTM D882
Yield stress TD	31	MPa	ASTM D882
Yield stress MD	33	MPa	ASTM D882
Modulus of elasticity MD	1250	MPa	ASTM D882
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Temperature</b>			
Vicat softening temperature	125	°C	ASTM D1525

- (1) Typical values: not to be construed as specification limits.  
(2) Properties are based on 15 µm film produced at 4 BUR using 100% F00952

## ENVIRONMENT AND RECYCLING

The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc. SABIC Europe considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials. Recycling of packaging materials is supported by SABIC Europe whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered. Whenever 'thermal' recycling of packaging (i.e. incineration with energy recovery) is carried out, polyethylene -with its fairly simple molecular structure and low amount of additives- is considered to be a trouble-free fuel.

## HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, available on the Internet ([www.SABIC-europe.com](http://www.SABIC-europe.com)). Additional specific information can be requested via your local Sales Office.

## QUALITY

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO 9001.

## STORAGE AND HANDLING

Polyethylenes resins (in pelletised or powder form) should be stored in such a way that it prevents exposure to direct sunlight and/or heat, as this may lead to quality deterioration. The storage location should also be dry, dust free and the ambient temperature should not exceed 50 °C. Not complying with these precautionary measures can lead to a degradation of the product which can result in colour changes, bad smell and inadequate product performance. It is also advisable to process polyethylene resins (in pelletised or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.